



## Original London Yellow Stock

|                             |                                                                                                                   |
|-----------------------------|-------------------------------------------------------------------------------------------------------------------|
| PRODUCT CODE                | SKU224                                                                                                            |
| BRICK TYPE                  | Handmade Brick                                                                                                    |
| SPECIFICATION               | BS EN 771-1                                                                                                       |
| SIZE                        | 65mm x 215mm x 102mm                                                                                              |
| DIMENSIONAL TOLERANCE       | TM                                                                                                                |
| RANGE                       | RM                                                                                                                |
| COMPRESSIVE STRENGTH        | Mean - 16.2 N/MM <sup>2</sup>                                                                                     |
| WATER ABSORPTION            | Mean - 20%                                                                                                        |
| SOLUBLE SALT CLASSIFICATION | S2                                                                                                                |
| DURABILITY                  | F2                                                                                                                |
| PACKAGING                   | Shrink wrapped on wooden pallets in packs of 400 bricks                                                           |
| PACK SIZE: L X W X H        | 1200mm x 1000mm x 900mm                                                                                           |
| PACK WEIGHT                 | 1000kg Approx                                                                                                     |
| USAGE                       | Always mix from several packs, working vertically down the blades, not horizontally across the tops of the packs. |

### PERFORMANCE

The recommendations of good practice made in the relevant British Standards regarding design and workmanship must be fully observed. Liability cannot be accepted for the performance of the product if used outside our recommendations. Guidance on the use of these bricks in specific situations is readily available from us.



For more information on products, services, advice and technical guidelines please contact our Sales Team.

[info@heritagebrickcompany.co.uk](mailto:info@heritagebrickcompany.co.uk)

0114 321 7899

[www.heritagebrickcompany.co.uk](http://www.heritagebrickcompany.co.uk)

Individual bricks may vary dimensionally; this is a natural characteristic of fired clay bricks and is catered for in BS EN 771-1. Technical data correct at time of issue. Always order samples before purchasing and follow good site practice guidelines.



LUCIDEON



UK  
CA