



Reclaimed Industrial Blend

PRODUCT CODE	SKU001
BRICK TYPE	Pressed Brick
SPECIFICATION	BS EN 771-1
SIZE	76mm x 228mm x 108mm or 3" x 9" x 4 1/4"
DIMENSIONAL TOLERANCE	TM
RANGE	RM
COMPRESSIVE STRENGTH	Mean - 109.5 N/MM ²
WATER ABSORPTION	Mean - 5%
SOLUBLE SALT CLASSIFICATION	S2
DURABILITY	F1
PACKAGING	Shrink wrapped on wooden pallets in packs of 400 bricks
PACK SIZE: L X W X H	1200mm x 1000mm x 900mm
PACK WEIGHT	1600kg Approx
USAGE	Always mix from several packs, working vertically down the blades, not horizontally across the tops of the packs.
PERFORMANCE	The recommendations of good practice made in the relevant British Standards regarding design and workmanship must be fully observed. Liability cannot be accepted for the performance of the product if used outside our recommendations. Guidance on the use of these bricks in specific situations is readily available from us.



For more information on products, services, advice and technical guidelines please contact our Sales Team.

info@reclaimedbrickcompany.co.uk

0114 206 1113

www.reclaimedbrickcompany.co.uk

Individual bricks may vary dimensionally; this is a natural characteristic of fired clay bricks and is catered for in BS EN 771-1. Technical data correct at time of issue. Always order samples before purchasing and follow good site practice guidelines.



LUCIDEON



UK
CA