

Reclaimed Wirecut Bricks

SKU004

1600kg Approx

PRODUCT CODE

PACK WEIGHT

PERFORMANCE

USAGE

SPECIFICATION BS EN 771-1	
SIZE 76mm x 228mm x 108mm or 3	3" x 9" x 4 1/4"
DIMENSIONAL TOLERANCE TM	
RANGE RM	
COMPRESSIVE STRENGTH Mean - 36.9 N/MM^2	
WATER ABSORPTION Mean -12 %	
SOLUBLE SALT CLASSIFICATION S1	
DURABILITY F2	
PACKAGING Shrink wrapped on wooden pa	allets in packs of 400 bricks
PACK SIZE: L X W X H 1200mm x 1000mm x 900mm	ı

The recommendations of good practice made in the relevant British Standards regarding design and workmanship must be fully observed. Liability cannot be accepted for the performance of the product if used outside our recommendations. Guidance on the use of these bricks in specific situations is readily

Always mix from several packs, working vertically down the blades, not horizontally across the tops of the



For more information on products, services, advice and technical guidelines please contact our Sales Team.

info@reclaimedbrickcompany.co.uk 0114 206 1113 www.reclaimedbrickcompany.co.uk

Individual bricks may vary dimensionally; this is a natural characteristic of fired clay bricks and is catered for in BS EN 771-1. Technical data correct at time of issue. Always order samples before purchasing and follow good site practice guidelines.







